

TECHNICAL DATA			
PROPERTIES		UNIT	BT~-MT
PHYSICAL			
Thickness		Micron	12
Yield		m ² /kg	96.34
Grammage		gm/m ²	10.38
OPTICAL			
Haze (Max)		%	80
Gloss at 45°		-	9
MECHANICAL			
Tensile Strength	(MD) Min	kg/cm ²	1150
	(TD) Min	kg/cm ²	2400
Elongation	(MD)	%	18
	(TD)	%	0
			55
COF Max		kinetic	0.32
THERMAL			
Shrinkage (120°C/5min)	(MD)	%	4.5
	(TD)	%	2.5
SURFACE			
Treatment level		Dyne/cm	38

TECHNICAL DATA			
PROPERTIES		UNIT	BT~ MT
PHYSICAL			
Thickness		Micron	15
Yield		m ² /kg	77.07
Grammage		gm/m ²	12.98
OPTICAL			
Haze (Max)		%	80
Gloss at 45°		-	9
MECHANICAL			
Tensile Strength	(MD) Min	kg/cm ²	1150
	(TD) Min	kg/cm ²	2400
Elongation	(MD)	%	180
	(TD)	%	55
COF Max (Untreated or lower tr/Untreated or lower tr)		kinetic	0.32
THERMAL			
Shrinkage (120°C/5min)	(MD)	%	4
	(TD)	%	2
SURFACE			
Treatment level		Dyne/cm	38